



Rynite® FR533NH NC010 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

Common features of Rynite® thermoplastic polyester include mechanical and physical properties such as excellent balance of strength and stiffness, dimensional stability, creep resistance, heat resistance, high surface gloss and good inherent electrical properties at elevated temperature. It can be processed over a broad temperature range and has excellent flow properties.

Rynite® thermoplastic polyester resins are typically used in demanding applications in the automotive, electrical and electronics, appliances where they successfully replace metals and thermosets, as well as other thermoplastic polymers.

Rynite® FR533NH NC010 is a 33% glass reinforced, modified polyethylene terephthalate resin using a non-halogenated flame retardant.

Product information

Resin Identification	PET-GF33FR(40)	ISO 1043
Part Marking Code	>PET-GF33FR(40)<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.3 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.7 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	13100 MPa	ISO 527-1/-2
Stress at break	85 MPa	ISO 527-1/-2
Strain at break	0.9 %	ISO 527-1/-2
Flexural Modulus	13000 MPa	ISO 178
Flexural Strength	143 MPa	ISO 178
Charpy notched impact strength, 23°C	11 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -40°C	11 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33 -	

Thermal properties

Melting temperature, 10°C/min	249 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	240 °C	ISO 75-1/-2
Ball pressure test	230 °C	IEC 60695-10-2
CLTE, Parallel, -40-23°C	18 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	18 E-6/K	ISO 11359-1/-2
CLTE, Parallel, 55-160°C	11 E-6/K	ISO 11359-1/-2
CLTE, Normal, -40-23°C	51 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	72 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, Normal, 55-160°C	81 E-6/K	ISO 11359-1/-2
RTI, electrical, 0.4mm	155 °C	UL 746B
RTI, electrical, 0.75mm	155 °C	UL 746B



Rynite® FR533NH NC010 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

RTI, electrical, 1.5mm	155 °C	UL 746B
RTI, electrical, 3mm	155 °C	UL 746B
RTI, impact, 0.75mm	160 °C	UL 746B
RTI, impact, 1.5mm	170 °C	UL 746B
RTI, impact, 3mm	170 °C	UL 746B
RTI, strength, 0.75mm	160 °C	UL 746B
RTI, strength, 1.5mm	170 °C	UL 746B
RTI, strength, 3mm	170 °C	UL 746B

Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10
UL recognition	yes -	UL 94
Burning Behav. at thickness h	V-0 class	IEC 60695-11-10
Thickness tested	0.4 mm	IEC 60695-11-10
UL recognition	yes -	UL 94
Burning Behav. 5V at thickness h	5VA class	IEC 60695-11-20
Thickness tested	0.75 mm	IEC 60695-11-20
UL recognition	yes -	UL 94
Glow Wire Flammability Index, 0.75mm	960 °C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960 °C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960 °C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	825 °C	IEC 60695-2-13
Glow Wire Ignition Temperature, 1.5mm	775 °C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3mm	850 °C	IEC 60695-2-13
Railway classification	R22 -	EN 45545-2
Railway classification rating	HL1 -	EN 45545-2

Electrical properties

Volume resistivity	1E13 Ohm.m	IEC 62631-3-1
Electric strength	34 kV/mm	IEC 60243-1
Comparative tracking index	350 -	IEC 60112
Comparative tracking index, 3.0mm	2 PLC	UL 746A

Other properties

Density	1610 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	≤0.02 ^[1] %
Melt Temperature Optimum	280 °C
Min. melt temperature	270 °C



Rynite® FR533NH NC010 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

Max. melt temperature	280 °C
Min. mould temperature	120 °C
Max. mould temperature	140 ^[2] °C

[1]: At levels above 0.02%, strength and toughness will decrease, even though parts may not exhibit surface defects.

[2]: (6mm - 1mm thickness)

Characteristics

Additives Flame retardant, Non-halogenated/Red phosphorous free flame retardant

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2021 DuPont. All rights reserved.