



Zytel® HTN50G35HSL NC010 (DEVELOPMENTAL)

HIGH PERFORMANCE POLYAMIDE RESIN

Zytel® HTN50G35HSL NC010 is a 35% glass reinforced, heat stabilised, lubricated, hydrolysis resistant high performance polyamide resin. It is also a PPA resin.

Product information

Resin Identification	PA-GF35	ISO 1043
Part Marking Code	>PA-GF35<	ISO 11469
Part Marking Code	>PPA-GF35<	SAE J1344

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	0.2/-	%	ISO 294-4, 2577
Moulding shrinkage, normal	0.5/-	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile Modulus	13200/-	MPa	ISO 527-1/-2
Stress at break	240/220	MPa	ISO 527-1/-2
Strain at break	2.5/2.3	%	ISO 527-1/-2
Flexural Modulus	-/11800	MPa	ISO 178
Flexural Strength	-/337	MPa	ISO 178
Charpy impact strength, 23°C	86/76	kJ/m ²	ISO 179/1eU
Charpy impact strength, -40°C	71/60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	13/12	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	12/-	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -40°C	12/12	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33/-	-	

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	302/*	°C	ISO 11357-1/-3
CLTE, Parallel, -40-23°C	17/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	18/*	E-6/K	ISO 11359-1/-2
CLTE, Normal, -40-23°C	53/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	57/*	E-6/K	ISO 11359-1/-2

Flammability

FMVSS Class	SE -	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	2.2 mm/min	ISO 3795 (FMVSS 302)



Zytel® HTN50G35HSL NC010 (DEVELOPMENTAL)

HIGH PERFORMANCE POLYAMIDE RESIN

Electrical properties

	dry/cond.		
Relative permittivity, 100Hz	4.9/-	-	IEC 62631-2-1
Relative permittivity, 1MHz	4.6/-	-	IEC 62631-2-1
Dissipation factor, 100Hz	31/-	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	149/-	E-4	IEC 62631-2-1
Volume resistivity	>1E13/>1E13	Ohm.m	IEC 62631-3-1
Surface resistivity	*/>1E15	Ohm	IEC 62631-3-2
Electric strength	42/41	kV/mm	IEC 60243-1
Comparative tracking index	600/-	-	IEC 60112

Other properties

	dry/cond.		
Density	1470/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	6 - 8 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	325 °C
Min. melt temperature	320 °C
Max. melt temperature	330 °C
Mold Temperature Optimum	150 °C
Min. mould temperature	140 ^[1] °C
Max. mould temperature	180 °C

[1]: higher temperature needed for thinner sections

Characteristics

Additives	Release agent
-----------	---------------

Additional Information

Injection molding During molding, use proper protective equipment and adequate ventilation. Avoid exposure to fumes and limit the hold up time and temperature of the resin in the machine. Purge degraded resin carefully with HDPE.


When lower mold temperatures are used, the initial warpage and shrinkage may be lower, but the surface appearance and chemical resistance may be reduced, and the dimensional change may be greater when parts are subsequently heated.



Zytel® HTN50G35HSL NC010 (DEVELOPMENTAL)

HIGH PERFORMANCE POLYAMIDE RESIN

Stress-strain (dry)






Zytel® HTN50G35HSL NC010 (DEVELOPMENTAL)

HIGH PERFORMANCE POLYAMIDE RESIN

Stress-strain (cond.)



Revised: 2021-05-04

Page: 4 of 4

dupont.com

The above data are for the developmental sample and are subject to change as the product is scaled up.

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2021 DuPont. All rights reserved.