

### Product Description

Ultramid A3W BK00464 is an easy flowing, pigmented black, heat aging resistant injection molding PA66 grade for fast processing.

### Applications

Typical applications include highly stressed parts such as bearings, bearing cages, gear-wheels, coil formers and cable connectors.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm <sup>3</sup>	1183	1.14	
Moisture, %	62		
(50% RH)		2.8	
(Saturation)		8.5	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23°C		3,300	-
Tensile stress at yield, MPa	527		
23°C		88	-
Tensile strain at yield, %	527		
23°C		4.7	-
Flexural Modulus, MPa	178		
23°C		3,100	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m <sup>2</sup>	180		
-40°C		4	-
23°C		4.5	-
Charpy Notched, kJ/m <sup>2</sup>	179		
-30°C		3	-
23°C		4.6	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, °C	3146	260	-
HDT A, °C	75	75	-
HDT B, °C	75	210	-
UL RATINGS	UL Test Method	Property Value	
Flammability Rating, 0.75mm	UL94	V-2	
Relative Temperature Index, 0.75mm	UL746B		
Mechanical w/o Impact, °C		105	
Mechanical w/ Impact, °C		105	
Electrical, °C		130	
Flammability Rating, 1.5mm	UL94	V-2	
Relative Temperature Index, 1.5mm	UL746B		
Mechanical w/o Impact, °C		105	
Mechanical w/ Impact, °C		105	
Electrical, °C		130	
Flammability Rating, 3.0mm	UL94	V-2	
Relative Temperature Index, 3.0mm	UL746B		
Mechanical w/o Impact, °C		110	
Mechanical w/ Impact, °C		105	
Electrical, °C		130	
Flammability Rating, 6.0mm	UL94	V-2	
Relative Temperature Index, 6.0mm	UL746B		
Mechanical w/o Impact, °C		110	
Mechanical w/ Impact, °C		105	
Electrical, °C		130	

### Processing Guidelines

#### Material Handling

Max. Water content: 0.20%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80 degC (176 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your BASF representative.

#### Typical Profile

Melt Temperature 280-300 degC (536-572 degF)

Mold Temperature 40-80 degC (104-176 degF)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

**Mold Temperatures**

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 40-80 degC (104-176 degF) is recommended.

**Pressures**

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

**Fill Rate**

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing.

**Note**

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation  
Engineering Plastics  
1609 Biddle Avenue  
Wyandotte, MI 48192

General Information: 800-BC-RESIN  
Technical Assistance: 800-527-TECH (734-324-5150)  
Web address: <http://www.plasticsportal.com/usa>

