

CYCOLOY™ FR RESINS CM6240

REGION ASIA

DESCRIPTION

CYCOLOY CM6240 Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) blend is an injection moldable non chlorinated/brominated mineral-filled flame retardant grade. It features high modulus, good flow, ductility and low warpage. It has a UL94 V0@0.8mm and 5VB@1.5mm flame rating and is a good candidate for thin wall applications.

TYPICAL PROPERTY VALUES

Revision 20190411

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	55	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	40	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	35	%	ASTM D638
Tensile Modulus, 5 mm/min	4350	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	96	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	4400	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	56	MPa	ISO 527
Tensile Stress, break, 5 mm/min	29	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	25	%	ISO 527
Tensile Modulus, 1 mm/min	4460	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	101	MPa	ISO 178
Flexural Modulus, 2 mm/min	4510	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	86	J/m	ASTM D256
Izod Impact, notched, -30°C	60	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	56	J	ASTM D3763
Instrumented Dart Impact Total Energy, -30°C	35	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	7	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	97	°C	ASTM D1525
HDT, 1.82 MPa, 6.4 mm, unannealed	90	°C	ASTM D648
CTE, -40°C to 40°C, flow	4.9E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.4E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	4.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	97	°C	ISO 306
Vicat Softening Temp, Rate B/120	100	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	86	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.3	-	ASTM D792

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, flow, 3.2 mm	0.3 – 0.4	%	SABIC method
Mold Shrinkage, flow	0.33	%	SABIC method
Mold Shrinkage, xflow	0.38	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	16.5	g/ 10 min	ASTM D1238
Density	1.3	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.1	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.03	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	15	cm ³ / 10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating	0.8	mm	UL 94 by SABIC-IP
UL Compliant, 94-5VB Rating	1.5	mm	UL 94 by SABIC-IP
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	>4 - 6	Hrs	
Drying Time (Cumulative)	16	Hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	255 – 285	°C	
Nozzle Temperature	255 – 285	°C	
Front - Zone 3 Temperature	255 – 285	°C	
Middle - Zone 2 Temperature	230 – 275	°C	
Rear - Zone 1 Temperature	220 – 255	°C	
Mold Temperature	70 – 95	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.